



PRODUCT DATA SHEET

Edition 05.2018/v1

CSC Master Format™ 03 62 13

NON-METALLIC, NON-SHRINK GROUTING

SikaGrout®-212

HIGH QUALITY, VERSATILE AND NON-SHRINK, CEMENTITIOUS GROUT

Description	SikaGrout®-212 is a non-shrink, cementitious grout with a unique two-stage shrinkage compensating mechanism, compensating for shrinkage in both the plastic and the hardened states. It is non-metallic, contains no chlorides and may be placed at various consistencies ranging from dry pack to fluid by simply adjusting the quantity of mixing water. A sulphate resistant grade, SikaGrout®-212 SR, and a silica fume modified grade, SikaGrout®-212 HP, are also available (see separate Product Data Sheets).
Where to Use	- On grade, above and below grade, interior and exterior applications. - Structural grouting of column base plates, machine base plates, anchor bolts, bearing plates, bridge seats, precast wall panels. - On grouting projects where ability to adjust consistency and achieve accelerated strength development is required.
Advantages	- Pre-blended for easy application and maximum field control. Just add water, mix and place. - Versatile, can be applied in any consistency from dry pack to fluid by varying water content. - Reducing water content accelerates strength development and ultimate compressive strength values. - Non-corrosive, does not contain chlorides. - Formulated with inert, non-reactive aggregates to eliminate potential Alkali-Aggregate Reactivity (AAR). - Excellent pumpability - does not segregate even at high flow; no build-up on equipment hopper. - Low heat development. - Superior freeze/thaw resistance. - Product qualified by <i>The Road Authority</i> (TRA). - Meets Ontario Hydro specification M-690-87 for pumping through grout pump and hoses for distances of up to 60 m (196 ft). <i>Ministère des Transports du Québec</i> (MTQ) acceptance for grouting anchor bolts and reinforcing dowels in concrete. - Approved by the Alberta Ministry of Transportation. - Product recognized by the British Columbia Ministry of Transportation (BC MoT). - Meets H. A. Simons grout specification 1S-05.01 for grout types 1, 2a, 2b, 2c, 3 and 4.

Technical Data

Packaging	25 kg (55 lb) bag				
Colour	Concrete Grey				
Yield	Approx. 13 L (0.46 ft³) per bag of fluid grout				
Shelf Life	12 months in original, unopened bag. Store dry, ensuring that product is not exposed to rain, condensation or high humidity. For best results, condition product at 18 to 29 °C (65 to 84 °F) before using.				
Mix Ratio	4.6 L (1.21 US gal.) water/bag max.				
Properties at 23 °C (73 °F) and 50 % R.H.					
SikaGrout®-212 (tested at water/solids ratio of 0.18 by weight)					
Aggregate grading ASTM C136	100 % passing 2.5 mm (3/32 in)				
Flow cone CAN/CSA A23.2-1B	< 30 s				
Placement Time	1 hour max.				
Set time ASTM C403	Initial Final	4 to 5 h 30 min 5 to 7 hours			
Hardened Expansion ASTM C1090 (28 days)					
> 0 – ≤ + 0.3 %					
Compressive Strength, MPa (psi)					
CAN/CSA A23.2-1B*	W/S = 0.18 [4.6 L (1.21 US gal.)/bag]				
1 day	26 (3770)				
3 days	42 (6095)				
7 days	48 (6965)				
28 days	56 (8125)				
Compressive Strength ASTM C109, MPa (psi)*					
(SikaGrout®-212 tested with Sikacem® Accelerator)					
Temperature	Dosage	24 hours	2 days	3 days	28 days
0 °C (32 °F)	1 bottle (150 mL)	2 (290)	13 (1932)	24 (3550)	41 (5946)
10 °C (50 °F)	1 bottle (150 mL)	18 (2624)	33 (4855)	40 (5756)	48 (6960)
23 °C (73 °F)	1 bottle (150 mL)	37 (5366)	42 (6070)	45 (6461)	56 (8125)

** Fluid consistency compressive strengths are given as minimum guidelines. Pourable and dry pack consistencies will easily exceed these values. All moulds, mixing tools and powder components were pre-conditioned to the test temperatures. Prepared test specimens were cast and then cured at the indicated test temperatures until the time of testing. Lid should be clamped on mold at all time. Liquid/solids ratio (water + Sikacem® Accelerator/SikaGrout®-212) = 0.18; [4.6 L (1.21 US gal.) of liquid per 25 kg (55 lb) bag of SikaGrout®-212].*

* Fluid consistency compressive strengths are given as minimum guidelines. Pourable and dry pack consistencies will easily exceed these values. All moulds, mixing tools and powder components were pre-conditioned to the test temperatures. Prepared test specimens were cast and then cured at the indicated test temperatures until the time of testing. Lid should be clamped on mold at all time. Liquid/solids ratio (water + Sikacem® Accelerator/SikaGrout®-212) = 0.18; [4.6 L (1.21 US gal.) of liquid per 25 kg (55 lb) bag of SikaGrout®-212].

SikaGrout®-212

Freeze/thaw durability ASTM C666, Procedure A

Relative dynamic modulus 101.9 %

Durability factor 101

No significant change to specimen

Anchor Bolt Grouting Applications

Water/solids ratio 0.166

Mix water 4.15 L (1.1 US gal.)

Pull-Out Results [38 mm (1.5 in) diameter hole]

Hole depth, mm (in)	Load failure, kN (lbf)	Comments
125 (5)	78.6 (17 670)	Concrete block split in half
190 (7.5)	108.2 (24 324)	Concrete block split in half
250 (10)	126.4 (28 416)	Concrete block split in half

Data based on results obtained from pull tests on 15 M, epoxy coated rebars grouted into 30 MPa (4350 psi), 80 ± 10 mm slump, 6 ± 1 % air entrained concrete block

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.

HOW TO USE**Surface****Preparation**

All grease, oil laitance, ice or snow and any foreign deposits shall be removed from all surfaces with which the grout will come in contact. The concrete foundation shall be roughened to the extent that it does not present a smooth surface, which would impede the bond of the grout to the foundation. All dust and loose particles shall be removed by sandblasting, high pressure waterblasting or other suitable means.

Concrete foundations less than 28 days old shall be kept wet for at least 12 hours, and older foundations for a minimum of 24 hours before placing grout (SSD condition). All free-standing water shall be removed from concrete surfaces prior to grouting. All items to be grouted into place shall be properly positioned and anchored prior to grouting except for anchor bolts and dowels, which may be placed into the fresh grout if job conditions permit and at the discretion of the engineer in charge. For grouting of base plates the formwork used to contain the grout shall be constructed in a workmanlike manner and caulked to prevent leakage of grout. Provisions shall be made at the high points for air to be vented as it is displaced by grout.

Mixing

Mix using a heavy duty low-speed drill (300 - 450 rpm) and mixing paddle (*Jiffy* or *Exomixer*®) or in a grout mixer. The size of the mixer should be appropriate to the volume of grout required. Use a minimum amount of water consistent with placeability requirements. After all dry product has been added to the water, continue mixing for three (3) minutes. For application greater than 150 mm (6 in) in thickness, add up to 12 kg (26.5 lb) of 10 mm (3/8 in) coarse aggregate. The aggregate must be non-reactive (reference ASTM C1260, C227, and C289), clean, well-graded, saturated surface dry, have low absorption, high density and comply with ASTM C33, size number 8 per table 2.

Application

The prepared grout may be pumped or transported to the forms in buckets or wheelbarrows and deposited without delay. External vibration and agitation of the grout in the forms is permitted. Grout having been prepared but not placed within one (1) hour after preparation shall be discarded. Prepared grout shall be agitated until use. Several hours after placement of grout (depending on ambient temperatures) forms may be removed and exposed grout shoulders may be trimmed or shaped to desired finish.

Dry pack application: Refer to the Sika Cementitious Grouting Method Statement.

Curing

As per ACI 308 recommendations for cement concrete, curing is required. To achieve performance consistent with Technical Data, curing must be provided by recognized curing methods, such as wet burlap covered with white polyethylene film, misting with water, or approved water-based curing compound, such as Sika® Florseal WB-18 & -25. Usage of Sika® Ultracure DOT™ or NCF™ wet curing blankets is also strongly recommended. Curing must commence immediately after placing and finishing. Protect freshly applied grout from direct sunlight, wind rain and frost.

Clean Up

Clean all tools and equipment immediately after use with water. Once hardened, material can only be removed manually or mechanically. Wash soiled hands and skin thoroughly in hot soapy water or use Sika® Hand Cleaner towels.

Limitations

- Important: protect stored material from exposure to rain, condensation and high humidity as moisture may penetrate packaging, causing lumps.
- For best results, condition product to temperatures ranging from 18 to 29 °C (65 to 84 °F) prior to mixing and installation. Lower temperatures may result in slower strength development and longer cure times.
- Maintain wet grout, ambient and substrate temperatures between 5 - 32 °C (41 - 89 °F) for a period of 72 hours after placing, unless using Sikacem® Accelerator in mix (refer to Technical Data section).
- SikaGrout®-212 must be protected from freezing during setting.
- Minimum application thickness (neat without additional aggregate): 25 mm (1 in).
- Maximum application thickness (neat without additional aggregate): 150 mm (6 in). Thicker applications are possible with the addition of suitable aggregate. Contact Sika Canada.
- For anchor bolt/dowel grouting, hole diameter should be 25 mm (1 in) greater than bar diameter.
- Anchor bolt/bar holes should be pre-dampened for a period of one (1) hour prior to grouting. Holes must be in saturated surface dry (SSD) condition at time of grouting.
- Do not use as a patching or overlay mortar or in unconfined areas.
- Use only potable water.
- Extending with aggregates will reduce compressive and flexural strengths. Dimensions and grading of aggregates will influence effect on physical properties; pre-testing is recommended.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent SAFETY DATA SHEET containing physical, ecological, toxicological and other safety-related data.

KEEP OUT OF REACH OF CHILDREN
FOR INDUSTRIAL USE ONLY

The Information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelflife. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

SIKA CANADA INC.

Head Office

601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9

Other locations

Toronto
Edmonton
Vancouver

1-800-933-SIKA
www.sika.ca

Certified ISO 9001 (CERT-0102780)
Certified ISO 14001 (CERT-0102791)



Distributed by:

Multicrete Systems Inc.
555 Kapelus Drive, West St. Paul Manitoba R4A 5A4
Phone: 204-262-5900
www.multicretesystems.com

